



TERA-GEM III

Superior Chemical Resistant Flooring System (CRS III)

PRODUCT DESCRIPTION

Tera-Gem III Superior Chemical Resistant Flooring System (CRS III) is a troweled tough wearing, 100% solids, solvent free (No VOC's – Meets all of California's VOC Requirements), seamless epoxy - aggregate composite designed for use as a chemical resistant overlayment for commercial and industrial environments. This product has excellent adhesion to concrete, tile and wood substrates. This product can also be installed to vertical surfaces and ceilings. The Tera-Gem III CRS system is a nominal 1/8" or 1/4" thick composite consisting of the following:

PRIMER: A two-component moisture tolerant epoxy primer. Other primers can be substituted depending on application.

BASE COAT: A three component, troweled polymer composite consisting of epoxy resin (with or without inorganic pigments), curing agent, and selected graded silica aggregates.

TWO SEAL COATS: Consists of the Tera-Gem III CRS III liquid components with inorganic pigments. Other sealers may be added depending upon application and texture demands.

PHYSICAL PROPERTIES

Compressive Strength	(ASTM C-579)	11,800 psi. AFTER 7 DAYS
Flexural Strength	(ASTM C-580)	5,000 psi.
Tensile Strength	(ASTM C-307)	2,800 psi.
Flammability	(ASTM 635)	Self Extinguishing
Impact Resistance	(Mil D-3134F Sec 4.7.3)	No cracking or delamination at 16/ft./lbs.
Water Absorption	(ASTM C-413)	0.25%
Bond Strength, Primer	(ASTM 4541)	>400 psi

Physical Properties-Binder Cured 7 days

Tensile Strength	(ASTM D 638) psi	6,000 psi
Flexural Strength	(ASTM D 790) psi	10,500 psi
Flexural Modulus	(ASTM D 790) psi	4.10 x 10 ⁻⁵
Hardness	(ASTM 2240)	Shore D - 84
Abrasion Resistance	(ASTM 4060) CS10 Wheel	1000 cycles, wt. loss (gm) - .041 gm

Application Properties

Mix Ratio	1A : 75B by volume
Pot Life (minutes)	20-50 @ 77 deg. F
Application Temp.	(F. Min) 50 deg .F

When placed by trained applicators, Tera-Gem III CRS III will provide a long lasting, easy to maintain floor that will stand up even in the most demanding of environments.

SUGGESTED USES

Tera-Gem III CRS III is suitable for plating shop, electronic plants, chemical plants and storage areas, laboratories, sewage and water treatment facilities, animal rooms, oil refineries, etc.

CHEMICAL RESISTANCE

Tera-Gem III CRS III is designed provide secondary containment, splash/spill resistance to a broad range of industrial chemicals. Including acids, alkalies, solvents and oxidizers. Consult the CRS III chemical resistance chart for specific recommendations. Contact the Tera-Lite, Inc. technical department for assistance.

NOTE:

- The end user should supply information regarding chemical concentrations, service temperatures and cleaning procedures to verify correct use of product. Review full chemical resistance charts for additional chemical information. Contact TL technical department for information regarding specific applications.
- Staining or a white blush will occur if the new floor is not allowed to cure fully (7 days) prior to allowing water, chemicals, etc. to stand on the surface.

SURFACE PREPARATION

Concrete surfaces must be free from surface contaminants, laitance, curing compounds, oils, greases, dirt, chemical contaminants, delaminated coatings, etc. The surface must be sound. Concrete compressive strength must be a minimum of 3,000 psi. New concrete should be cured for a minimum of 28 days. Wet curing is the preferred method. User must notify manufacturer if conditions differ from above. To properly clean concrete surfaces, the concrete may be sandblasted, steel shot-blasted, scarified, or other approved technique.

SYSTEM APPLICATION

PRIMER:

Use Tera-Gem III CRS III liquid A & B components as primer. Use a clean bucket and mix 2 parts of A to 1 part of B by volume. Stir with a mechanical agitator for 1-2 minutes. Distribute mixed material evenly over the floor surface using rollers or squeegees. Spread rate will vary from 70 to 150 sq. ft. per gallon depending on surface. Do not apply over standing water or let primer set before applying the base coat (aka body coat, troweled coat).

BASECOAT (aka Body Coat, Troweled Coat):

Use a clean container and mix Tera-Gem III CRS III liquid components at a ratio to 2 parts A to 1 part B by volume. To one weight equivalent of mixed liquid components add approximately 7 weight equivalent of aggregate. Mix all components using an electrical drill motor agitator or a plaster mixer. Mix all components for 2-3 minutes or until uniformly mixed. Transfer to installation area and trowel to a thickness of 1/8" to 1/4". Other thicknesses are possible.

SEALERS/ANTI-SKID:

To seal the epoxy/aggregate composite for easier cleaning and to assure a non-skid property, apply two pigmented seal coats using the Tera-Gem III CRS III liquid components. Mix in the same manner as described in the primer step. Apply the first seal coat (aka flood coat). Let the surface cure. Prep floor between coats by sanding the surface. Mix and place the second seal coat (aka topcoat) similarly to the first coat, application rate is approx. 125 sq. ft. per gallon. During the second seal coat process, if an anti-skid is required, incorporate graded silica aggregate to desired texture. See anti-skid recommendations for texture options.

MATERIAL HANDLING

Epoxy resins and curing agents have certain handling hazards. Users should become familiar with the information contained in the MSDS sheets for each formulated systems. Observe warning indications on the labels for each component.

PACKAGING

Tera-Gem III CRS III epoxy system is available in pre-measured gallon, 3 gallon kits, 15 gallons kits and 165 gallon kits.

NOTES

The following information is available online at www.teralite.com:

- Material Safety Data - Color Selection - Anti-Skid Recommendation -Maintenance Suggestions
- Chemical Resistance

The technical data furnished is true and accurate to the best of our knowledge. However, no guarantee of accuracy is given or implied. We suggest that the user evaluate these recommendations and suggestions in conjunction with their specific application. Tera-Lite, Inc. / Revolan Systems warrant its products to be free from manufacturing defects conforming to our most recent material specifications. In the event of liability, we will be limited to the replacement of material at the material value only and at the sole discretion of Tera-Lite Inc. /Revolan Systems. We assume no responsibility for coverage, suitability of application, performance, or injuries resulting from use.

REVOLAN SYSTEMS IS THE FORMULATING DIVISION OF TERA-LITE.